

Conference Proceedings Paper



Escherichia virus MS2, mimetic of SARS-CoV-2, inhibition via essential oils-loaded nanofibers: a potential formulation for antivirus individual protection masks

Samira F. da Silva, Joana Domingues, Joana C. Antunes and Helena P. Felgueiras

Centre for Textile Science and Technology (2C2T), University of Minho, Campus de Azurém 4800-058 Guimarães, Portugal

Abstract: In December 2019, a novel strain of coronavirus, SARS-CoV-2, was identified. Infected patients revealed symptoms of fever, cough (dry), sore throat, and fatigue, which began manifesting after 5 days of incubation. Hoping to prevent transmission, many countries adopted a mandatory mask use in closed public spaces. However, most mask options display a passive action against COVID-19. To overcome such restrictions, this work proposes the incorporation of anti-viral essential oils (EOs) loaded onto a nanofibrous layer that can be adapted to both community and commercial masks.

Twenty EOs selected based on their antimicrobial nature were examined for the first time against the Escherichia virus MS2. The most effective were the lemongrass (LO), Niaouli (NO) and eucalyptus (ELO) with a minimum inhibitory concentration (MIC) of 356.0 mg/mL, 365.2 mg/mL and 586.0 mg/mL, respectively. Polycaprolactone (PCL) and cellulose acetate (CA) were prepared individually at 14 wt% in chloroform/dimethylformamide (DMF) and 10 wt% in acetone/DMF, respectively, and combined at 3:1 ratio. Polymeric solutions were then processed via eletrospinning with processing parameters being optimized to 24.7 kV, 3.2 mL/h and 21 cm. Uniform, beadless nanofibers were obtained. Mats were characterized as mechanically resilient, to endure movements arising from mask positioning, and hydrophobic in nature, to repel droplets coming from the exterior. Loading of the nanofibrous mats was accomplished via physisorption using the free -OH groups of the CA as linkers. Mats were loaded with the EOs at MIC concentration for 72 h (saturation). Presence of the EOs was confirmed along the mats. Antimicrobial testing via halo determination, verified their diffusion abilities. More importantly, time-kill kinetics testing of the loaded mats attested to the EOs capability to fight the virus MS2 even when bonded to the nanofibers. Data demonstrated the potential of these EOs-loaded PCL/CA nanofibers mats to work as COVID-19 active barriers for individual protection masks.

Keywords: eletrospinning; hydrophobic barrier; mechanical resistance; antimicrobial; fighting covid-19 virus

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



© 2019 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license (http://creativecommons.org/licenses/by/4.0/).