

Universidade do Minho

Escherichia virus MS2, mimic of SARS-CoV-2, inhibition via essential oils-loaded nanofibers: a potential formulation for antivirus protection masks



CENTRO DE CIÊNCIA E TECNOLOGIATÊXTIL

www.2c2t.uminho.pt

Samira F. da Silva, Joana Domingues, Joana C. Antunes and Helena P. Felgueiras

Centro de Ciência e Tecnologia Têxtil (2C2T), Universidade do Minho, Portugal *helena.felgueiras@2c2t.uminho.pt

Introduction

In December 2019, a novel strain of coronavirus, SARS-CoV-2, was identified. Infected patients revealed symptoms of fever, cough (dry), sore throat, and fatigue, which began manifesting after 5 days of incubation. Hoping to prevent transmission, many countries adopted a mandatory mask use in closed public spaces. However, most mask options display a passive action against COVID-19. To overcome such restrictions, this work proposes the incorporation of anti-viral essential oils (EOs) loaded onto a nanofibrous layer that can be adapted to both community and commercial masks.

EOs Drawbacks

- cytotoxic at increased concentrations, which prevents systemic delivery;
- present low resistance to degradation by external factors (e.g., temperature, light, moisture);
- highly volatile in their free, unloaded form.

Results and Discussion

Minimum inhibitory Concentrations (MIC)

List of most effective oils:

| EOs | MS2 vírus (mg/mL) |
|------------|-------------------|
| Lemongrass | 356.0 |
| Niaouli | 365.2 |
| Eucalyptus | 586.0 |

Nanofiber Morphology and Diameters





Polymeric solution preparation

Polycaprolactone (PCL)



Cellulose Acetate (CA)



PCL 14% wt in chloroform/dimethyl formamide (9/1 v/v) PCL/CA 14%/10%wt (3/1 ratio) in acetone/dimethyl formamide (2/1 v/v)

╋

Degree of Swelling (DS) and Hydrophobicity

DS determined in simulated body fluid:

- DS of PCL = 74.84%-
- DS of PCL/CA = 55.30%

Hydrophobicity in distilled water



EOs Incorporation and Antimicrobial Testing (ongoing) Mats were loaded with the EOs at MIC concentration by immersing the mats for 72 h (saturation). Antimicrobial testing via halo determination, verified their diffusion abilities. More importantly, time-kill kinetics testing of the loaded mats attested to the EOs capability to fight the virus MS2 even when bonded to the nanofibers – data based on one repetition (require confirmation).

Processing conditions

PCL = 12.0 kV, speed of 0.7 mL/h, and 17 cm of distance to collector. PCL/CA = 24.7 kV, speed of 3.2 mL/h, and 21 cm of distance to collector

EOs Minimum Inhibitory Concentrations (MICs)

20 EOs were tested – selected based on their antimicrobial action: Amyris; Cajeput; Cinnamon leaf; Citronella; Clove; Eucalyptus; Frankincense; Geranium; Himalayan cedar; Lavandin; Lemongrass; Niaouli; Orchid; Palmarosa; Patchouli; Rosemary; Sage; Star anise; Tea tree oil; Wintergreen.

Conclusions: Data demonstrated the potential of these EOs-loaded PCL/CA nanofiber mats to work as COVID-19 active barriers for individual protection masks.

Acknowledgments

This work is financed by FEDER funds through COMPETE and by national funds through FCT via the projects POCI-01-0145-FEDER-028074 and UID/CTM/00264/2021.

