

Ultrasensitive Raman spectroscopy-based virus detection using glycan-coated plasmonic substrates[†]

Ojodomo J. Achadu ^{1*} and Enoch Y. Park²

¹ School of Health and Life Sciences, and National Horizon Centre, Teesside University, TS1 3BA, Middlesbrough, UK.

² Institute for Green Science and Biotechnology, Shizuoka University, Japan.

* Correspondence: O.Achadu@tees.ac.uk

† Presented at the title, place, and date.

Abstract: Hepatitis viral infections are the most common cause of hepatitis liver disease, which eventually leads to cancer and fibrosis if undetected early. Therefore, early detection would allow for preventive and therapeutic actions. Here, a surface-enhanced Raman spectroscopy (SERS)-based biosensor was developed using plasmonic molybdenum trioxide quantum dots (MoO₃-QDs) as the SERS substrates. The nanostructured substrate of MoO₃-QDs was functionalized with a proteoglycan (Syndecan-1) as a novel bioreceptor for target hepatitis E virus (HEV). The innovative bio-detection system achieved a detection limit of 1.05 fg/mL for tested HEV target (ORF2), indicating superb clinically relevant sensitivity and performance. The designed biosensing system incorporating a glycan motif as a bioreceptor instead of the conventional antibodies or aptamers, presents new insights for the ultrasensitive detection of HEV and other infectious viruses.

Keywords: Raman spectroscopy; diagnostic biosensor; hepatitis virus; glycans; plasmonic quantum dots

1. Introduction

Viral infections are the most common cause of liver disease, which eventually leads to cancer and fibrosis, irreparably destroying the liver [1]. As we all know, diseases that are detected and treated at an early stage are more likely to be effectively and successfully treated. Furthermore, point-of-care diagnostics have the potential to significantly enhance healthcare in both urban and rural settings resulting in fast turnaround times [2]. Compared to other diseases, early and rapid liver disease diagnostics are particularly underdeveloped. Since viral infections from hepatitis viruses are the most common cause of liver disease, the sensitive detection of these viruses in clinical specimen would allow for early preventive actions.

In this light, we have developed diagnostic biosensors for the detection of hepatitis E virus using Raman, fluorescence, and colorimetric techniques [3-5] as well as electrochemical systems [6,7] integrating functional nanoparticles and quantum dots. However, most of our previous studies and those in the literature have relied heavily on the use of antibodies and/or aptamers as hepatitis virus target bioreceptors [3-7]. This has implications in terms of cost, sensitivity, and specificity of developed assays, necessitating the need for alternative bioreceptors that can improve target virus captures and immunoassays. In this regards, nucleic acids, lectins, molecularly imprinted polymer/nanogels (artificial antibodies) and glycans have been highlighted as the next generation of bioreceptors [8-11]. Despite their promising performances, they are still less often employed and not fully developed. The incorporation of these new class of bioreceptors into biosensors design technology might bring new opportunities and tackle some inherent drawbacks of conventional bioreceptors antibodies and aptamers.

Citation: To be added by editorial staff during production.

Academic Editor: Firstname
Lastname

Published: date

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Copyright: © 2022 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).

Here, a novel Raman-based biosensor with a proteoglycan motif as a bioreceptor for targeting and detecting HEV ultrasensitively is developed. The rationale for using syndecan-1, a specific proteoglycan, as a biotargeting receptor stems from its high affinity and specificity for the capsid ORF2 protein of HEV, which can result in outstanding performance of the SERS-based HEV biosensor in terms of the analytical figures of merit such as limit of detection (LOD) and selectivity. The working principle is based on a surface-enhanced Raman scattering (SERS) mechanism. The detection protocol is based on the proprietary SERS nanotags system which we developed previously employing plasmonic molybdenum trioxide quantum dots (MoO₃-QDs)/4-mercaptobenzoic acid (4-MBA) nanotags [3,12]. The bio-assay platform provided a significant advance in the SERS enhancement factor of the nanotags up to 10⁹ and a femtogram level (1.05 fg/mL) of HEV analyte detection. This is ascribed to the specificity and sensitivity of the incorporated glycan recognition motif that may indicate clinically relevant specificity and accuracy.

2. Materials and Methods

Details of SERS measurement procedures and materials such as plasmonic MoO₃-QDs, nanotags preparation and characterization are described in our previous work [3, 12-14]. Biological materials - syndecan proteoglycan-1 was supplied by ACRO Biosystems (Newark, USA). Recombinant HEV (genotype 1) capsid protein (ORF2) was supplied by the Native Antigen (Oxford, UK). 4-Mercaptobenzoic acid (4-MBA) reporter molecule was purchased from Merck. All other chemicals and reagents were purchased from commercial suppliers and used as received.

The following were prepared. (1) Syndecan-1 conjugated 4MBA-MoO₃-QDs nanotags by incubating 2µg/mL of syndecan-1 with 1 mg/mL of 4MBA-MoO₃-QDs in PBS pH 7.2. (2) Glycan-coated glass slides by drop-casting of syndecan proteoglycan-1 solution on freshly cleaned slides [12].

The SERS bioassay of HEV was carried out by firstly optimizing all detection parameters followed by a series of bioreaction steps. Briefly, 100 µL of syndecan-1-4MBA-MoO₃-QDs nanotags was incubated with various amounts of recombinant HEV capsid protein in microtubes. After a reaction time of 30 mins, the HEV-nanotags were sequentially transferred to the prepared proteoglycan (syndecan 1)-coated substrates for Raman measurements. Selectivity studies followed similar protocol for HEV.


3. Results and discussion

The design and operational principle of the HEV biosensor in this work is depicted in Scheme 1. The HEV-specific detection mechanism was initiated by the reactivity of the recombinant HEV capsid protein as the target, with the syndecan-1-4MBA-MoO₃-QDs nanotags. A sandwich biocomplex was formed upon the deposition of the HEV-captured syndecan-1-4MBA-MoO₃-QDs nanotags on the syndecan-1-coated glass substrates. The immobilization of the HEV-syndecan-1-4MBA-MoO₃-QDs nanotags created SERS "hotspots" on the substrates which enabled the fast and efficient SERS detection of target HEV via the modulation of the Raman signal of the reporter molecule, 4MBA (Figure 1). The syndecan-1-HEV-syndecan-1-4MBA-MoO₃-QDs biocomplexes formed on the substrates were observed to increase proportionally with the concentration of the mediating HEV analyte resulting in the sequential Raman signal amplification of the reported molecule through SERS effect [12, 13]. A calibration plot resulting from the modulated Raman signal versus HEV concentration levels showed a linear dynamic range from 10 to 10⁶ fg/mL (Figure 2). The LOD was evaluated using the log-log calibration plot according to our earlier reported method [14]. Details in Fig. S11 of the Supplementary data S10 of [14]. The calculated LOD was 1.05 fg/mL which demonstrates the ultrasensitivity of the bioassay for the target HEV.

The presence and proximity of the plasmonic MoO₃-QDs to the reporter (4-MBA) and the HEV analyte synergizes the observed SERS effects possibly via both chemical and

electromagnetic enhancement mechanisms [13, 15]. The cumulative SERS enhancement factor was calculated to be $\sim 10^9$ demonstrating the robust nature of the SERS nanotags and substrates combination deployed in this work. The operational appraisal of the biosensor in terms of specificity and selectivity was evaluated by screening other viral antigens such as noro virus, influenza A virus, chikungunya E1 protein and SARS-CoV-2 spike protein. The result, as shown in Figure 3, demonstrated that the developed biosensor is highly selective for the target HEV.

3.1. Schemes and Figures



Scheme 1. Illustrative representation of the 4MBA-MoO₃-QDs nanotag functionalization with syndecan-1 (proteoglycan) and sandwiched capturing of HEV analyte on the syndecan-1-coated SERS substrate for HEV detection.




Figure 1. SERS spectra of the nanotag generated in the presence of different concentration of HEV capsid protein.




Figure 2. Corresponding calibration plot for proteoglycan (syndecan-1)-coated substrate bioassay of HEV capsid protein in PBS.




Figure 3. Selectivity results for HEV capsid protein detection compared to other viral targets using the proteoglycan (syndecan-1)-based SERS biosensor.

4. Conclusion

In summary, this work is based on the modification of plasmonic MoO₃-QDs-4MBA SERS nanotags with a proteoglycan (syndecan-1)-based bioreceptor for the detection of viral hepatitis target. Overall, the biosensing system demonstrated a strong potential for ultrasensitive HEV detection, making the biosensor suitable for early HEV testing. A further advancement is being investigated for the detection of HEV in low-volume serum samples for clinical HEV infection screening. Importantly, by incorporating a portable/handheld Raman device for diagnostic output, the developed bioassay may be deployed in hospitals and local clinics for routine viral hepatitis screening.

Author Contributions: OJA; conceptualization, methodology, validation, execution of experiments, manuscript preparation; EYP; validation, data curation, review, and editing. All authors have read and agreed to the published version of the manuscript.

Funding and Acknowledgments: Funding supports from the European Union's Horizon 2020 research and innovation program under the Marie Skłodowska-Curie grant agreement no. 945380 and the Japan Society for the Promotion of Science are gratefully acknowledged. Funding received from the Seed Corn R&I Programme of the School of Health and Life Sciences; Teesside University is gratefully acknowledged.

Institutional Review Board Statement: Not Applicable.

Informed Consent Statement: Not Applicable.

Data Availability Statement: Available on request.

Conflicts of Interest: The authors declare no conflict of interest.

References

1. Miyake Y, Kobashi H, Yamamoto K. Meta-analysis: The effect of interferon on development of hepatocellular carcinoma in patients with chronic hepatitis B virus infection. *J Gastroenterol.* 2009; 44:470–475.

2. Vashist SK. Point-of-Care Diagnostics: Recent Advances and Trends. *Biosensors* (Basel). 2017 Dec 18;7(4):62. doi: 10.3390/bios7040062.
3. Ojodomo J. Achadu, Fuyuki. Abe, Tiang C. Li, Indra M. Khoris, Dong. Lee, Jaebom. Lee, Tetsuro Suzuki and Enoch Y. Park. Molybdenum Trioxide Quantum Dot-Encapsulated Nanogels for Virus Detection by Surface-Enhanced Raman Scattering on a 2D Substrate, *ACS Applied Materials and Interfaces*, (2021) 13, 27836.
4. Akhilesh Babu Ganganboina, Ankan Dutta Chowdhury, Indra Memdi Khoris, Ruey-an Doong, Tian-Cheng Li, Toshimi Hara, Fuyuki Abe, Tetsuro Suzuki, Enoch Y. Park, Hollow magnetic-fluorescent nanoparticles for dual-modality virus detection, *Biosensors and Bioelectronics*, 2020,170, 112680, <https://doi.org/10.1016/j.bios.2020.112680>.
5. Khoris IM, Chowdhury AD, Li TC, Suzuki T, Park EY. Advancement of capture immunoassay for real-time monitoring of hepatitis E virus-infected monkey. *Anal. Chim. Acta*. 2020 May 8; 1110:64-71. doi: 10.1016/j.aca.2020.02.020.
6. Ganganboina AB, Khoris IM, Chowdhury AD et al (2020) Ultrasensitive detection of the hepatitis E virus by electrocatalytic water oxidation using Pt-Co3O4 hollow cages. *ACS Appl Mater Interfaces* 12:50212–50221. <https://doi.org/10.1021/acsami.0c13247>.
7. Chowdhury, A.D., Takemura, K., Li, TC. et al. Electrical pulse-induced electrochemical biosensor for hepatitis E virus detection. *Nat Commun* 10, 3737 (2019). <https://doi.org/10.1038/s41467-019-11644-5>.
8. Arezoo Saadati, Soodabeh Hassanpour, Miguel de la Guardia, Jafar Mosafer, Mahmoud Hashemzaei, Ahad Mokhtarzadeh, Behzad Baradaran, Recent advances on application of peptide nucleic acids as a bioreceptor in biosensors development, *TrAC Trends in Analytical Chemistry*, 114, 2019, 56-68. <https://doi.org/10.1016/j.trac.2019.02.030>.
9. Yaghoubi M, Rahimi F, Negahdari B, Rezayan AH, Shafiekhani A. A lectin-coupled porous silicon-based biosensor: label-free optical detection of bacteria in a real-time mode. *Sci Rep*. 2020 Sep 29;10(1):16017. doi: 10.1038/s41598-020-72457-x.
10. Cakir P, Cutivet A, Resmini M, Bui BT, Haupt K. Protein-size molecularly imprinted polymer nanogels as synthetic antibodies, by localized polymerization with multi-initiators. *Adv Mater*. 2013 Feb 20;25(7):1048-51. doi: 10.1002/adma.201203400.
11. Baker, A. N.; Richards, S.-J.; Guy, C. S.; Congdon, T. R.; Hasan, M.; Zwetsloot, A. J.; Gallo, A.; Lewandowski, J. R.; Stansfeld, P. J.; Straube, A. The SARS-COV-2 Spike Protein Binds Sialic Acids and Enables Rapid Detection in a Lateral Flow Point of Care Diagnostic Device. *ACS Cent. Sci*. 2020, 6, 2046–2052, DOI: 10.1021/acscentsci.0c00855.
12. Ojodomo J. Achadu, Fuyuki Abe, Tetsuro Suzuki, Enoch Y. Park. Molybdenum Trioxide Nanocubes Aligned on a Graphene Oxide Substrate the Detection of Norovirus by Surface-enhanced Raman Scattering, *ACS Applied Materials and interfaces*, (2020) 12(39), 43522-43534.
13. Ojodomo J. Achadu, Njemuwa Nwaji, Dongkyu Lee, Jaebeom Lee, Eser M. Akinoglu, Michael Giersig, Enoch Y. Park. 3D hierarchically porous magnetic molybdenum trioxide@gold nanospheres as a nanogap-enhanced Raman scattering biosensor for SARS-CoV-2, *Nanoscale Advances*, (2022), 4, 871-883.
14. Ojodomo J. Achadu, Fuyuki. Abe, Farzana. Hossain, Fahmida. Nasrin, Masahito. Yamazaki, Tetsuro. Suzuki and Enoch Y. Park. Sulfur-doped carbon dots@polydopamine-functionalized magnetic silver nanocubes for dual-modality detection of norovirus, *Biosensors and Bioelectronics* (2021), 193, 113540.
15. J. Zhang, Y. Pan, Y. Chen and H. Lu, Plasmonic molybdenum trioxide quantum dots with noble metal-comparable surface enhanced Raman scattering. *J. Mater. Chem. C*, 2018, 6, 2216.