

Proceeding Paper

A novel trigonometric high-order shear deformation theory for free vibration and buckling analysis of carbon nanotube reinforced beams resting on a Kerr foundation[†]

Mohammed Amine Kenanda^{1,*} and Fodil Hammadi²

¹ ENERGARID Laboratory, Department of Mechanical Engineering, Tahri Mohamed University, 08000 Bechar, Algeria; kenandaamine@gmail.com or kenanda.mohammedamine@univ-bechar.dz

² Laboratory of Mechanics, Modeling and Experimentation L2ME, Department of Mechanical Engineering, Tahri Mohamed University, 08000 Bechar, Algeria; hammadi.fodil@univ-bechar.dz

* Correspondence: kenandaamine@gmail.com or kenanda.mohammedamine@univ-bechar.dz

† Presented at the title, place, and date.

Abstract: This research is concerned with the free vibration and buckling analysis of carbon nanotube-reinforced beams (CNT-RBs) using a novel high-order shear deformation theory (HSDT). The current HSDT is modeled by a trigonometric function without a shear correction factor, and the displacement field has only four variables. Several different carbon nanotube distributions, including two uneven CNT distributions (X-CNT and O-CNT), are considered. The mixture rule is applied to express the effective material properties of carbon nanotube-reinforced beams. The CNTR beams are rested on two springs and a shear layer (Kerr foundation). Hamilton's principle is employed to derive the governing equations, which are then solved using the Navier technique. The current theory and several parameter effects are studied and validated in comparison to benchmark studies and theories. The main purpose of this study is to enhance understanding of high-order shear theories, such as third order, sinusoidal, exponential, etc. In this context, our theory yields excellent results when compared to other theories. The difference between our theory and the exact solution is so minimal that it is superior to other theories. The second part of the study focuses on investigating the distribution of carbon nanotubes to enhance understanding. This knowledge can assist panel manufacturers in determining the appropriate distribution shape. Our results indicate that the third distribution (X-CNT) significantly influences the mechanical behavior, unlike the first and second distributions (UD-CNT and O-CNT).

Keywords: carbon nanotube-reinforced beams; free vibration and buckling analysis; high-order shear deformation theory

Citation: To be added by editorial staff during production.

Academic Editor: Firstname Last-name

Published: date



Copyright: © 2023 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).

1. Introduction

Emerging materials like carbon nanotube-reinforced composites have a huge potential for use in high-tech industries, especially those like aerospace that demand advanced mechanical properties. Quality, sturdiness, dependability, and overall effectiveness can all be enhanced by adding carbon nanotubes to conventional matrices [1].

Recently, numerous research studies have focused on analyzing the behavior of beams constructed from carbon nanotube-reinforced composites. We will mention some of these studies in references [2-6].

In the context of advancing our understanding and obtaining results related to high-order shear deformation theories, which constitutes the primary objective of this paper, several prior theories were employed. These include the third-order theory developed by Reddy [7], the sinusoidal HSD theory by Touratier [8], the exponential HSD theory

introduced by Karama et al. [9], the hyperbolic HSD theory by Kenanda et al. [10], and the trigonometric-exponential HSD theory, also developed by Kenanda et al. [11-12].

This article will concentrate solely on the key points and fundamental equations that elucidate the novelty presented in this work. Detailed specifics will not be provided in this article, as the complete scope of our work will be published in an independent journal following our participation in the conference.

2. Material properties of CNTR Beams

Take into account the reference frame consisting of coordinates (x , y , and z) for a CNTR beam, characterized by its dimensions: width (b), length (L), and thickness (h). This beam is mounted on the Kerr foundation as depicted in Figure 1.




Figure 1. Carbon nanotube-reinforced beam resting on Kerr foundation: (a) Coordinate system for the CNTR beam and (b) three patterns of CNT distribution.

Based on the rule of mixture, material properties such as Young’s modulus, mass density, and Poisson’s ratio can be defined as:

$$E_{11} = \eta_1 V_{CNT} E_{11}^{CNT} + V_m E^m \tag{1a}$$

$$\frac{\eta_2}{E_{22}} = \frac{V_{CNT}}{E_{22}^{CNT}} + \frac{V_m}{E^m} \tag{1b}$$

$$\frac{\eta_3}{G_{22}} = \frac{V_{CNT}}{G_{12}^{CNT}} + \frac{V_m}{G^m} \tag{1c}$$

$$\nu = V_{CNT} \nu^{CNT} + V_m \nu^m \tag{1d}$$

$$\rho = V_{CNT} \rho^{CNT} + V_m \rho^m \tag{1e}$$

$$V_{CNT} + V_m = 1 \tag{1f}$$

Where ($E_{11}, E_{22}, G_{22}, \rho, \nu$) are the homogenized material properties of the composite and (V_m and V_{CNT}) are the volume fractions of matrix and carbon nanotubes, respectively. The latter is determined through the equations shown in the table 1, according to the

appropriate distribution. In addition, (η_1, η_2, η_3) are efficiency parameters of carbon nanotubes and matrix.

Table 1. The volume fraction of several patterns of CNT distribution.

Patterns of CNT distribution	V_{CNT}	V_{CNT}^*
UD-CNT	$V_{CNT} = V_{CNT}^*$	
O-CNT	$V_{CNT} = 2 \left(1 - 2 \frac{ z }{h} \right) V_{CNT}^*$	$V_{CNT}^* = \frac{W_{CNT}}{W_{CNT} + (\rho^{CNT} / \rho^m)(1 - W_{CNT})}$
X-CNT	$V_{CNT} = 4 \frac{ z }{h} V_{CNT}^*$	

In which (W_{CNT}) denotes the mass fraction of CNT.

3. Mathematical formulation

3.1. Displacement and strain field

High-order shear deformation beam theory provides the displacements along the x and z directions as follows:

$$\begin{aligned}
 u(x, z, t) &= u(x, t) - z \frac{\partial w(x, t)}{\partial x} + F(z) \phi(x, t) \\
 w(x, z, t) &= w(x, t)
 \end{aligned}
 \tag{2a}$$

In which

$$\phi(x, t) = \left(\frac{\partial w}{\partial x} - \varphi \right)
 \tag{2b}$$

Where $(u$ and $w)$ are the displacements along the x and z axes of the CNTR beam, and (φ) presents the rotation of the cross section. In which $F(z)$ is shape function that expresses the transverse shear stress distribution in a parabolic manner called the high-order shear theory. There are many functions that have been developed in this regard. We show the most important of them in Table 2.

Table 2. Present the most important beam theories.

Theories	The shape function $F(z)$
Euler–Bernoulli beam theory (classical beam theory)	$F(z) = 0$
Timoshenko beam theory (first-order shear theory)	$F(z) = z$
Third-order shear deformation theory [7] (high-order theory)	$F(z) = z \left(1 - \frac{4z^2}{3h^2} \right)$
Sinusoidal shear deformation theory [8] (high-order theory)	$F(z) = \frac{h}{\pi} \sin \left(\frac{\pi z}{h} \right)$

Exponential shear deformation theory [9]
(high-order theory)

$$F(z) = z \exp\left(-2\left(\frac{z}{h}\right)^2\right)$$

Trigonometric shear deformation theory (Present)
(high-order theory)

$$F(z) = \frac{\theta_1 h \left(\arctan(\sinh(z/h)) + \operatorname{sech}(z/h) \tanh(z/h) \right)}{2 \operatorname{sech}^3(1/2)} - \theta_1 z$$

$$\theta_1 = \frac{\operatorname{sech}^3(1/2)}{1 - \operatorname{sech}^3(1/2)}$$

According to equation (2), the strain field can be obtained in the following form:

$$\begin{aligned} \varepsilon_{xx} &= \frac{\partial u}{\partial x} - z \frac{\partial^2 w}{\partial x^2} + F(z) \frac{\partial \phi}{\partial x} \\ \gamma_{xz} &= \frac{dF}{dz} \phi \end{aligned} \tag{3}$$

Where (ε_{xx} and γ_{xz}) are the components of the strain tensor.

5. Results and discussion

In this section, our focus is on assessing the reliability and efficiency of the present trigonometric high-order shear deformation theory by contrasting it with various established theories. At the same time, we are investigating how the different CNT distributions influence the behavior of the CNRT (Carbon Nanotube Reinforced) beam. The mechanical characteristics employed in this section are outlined in Table 3.

Table 3. Present the material properties of CNT and matrix.

Material properties	CNT	Material properties	Matrix
E_{11}^{CNT} (GPa)	600	E^M (GPa)	2.5
E_{22}^{CNT} (GPa)	10	ρ^M (GPa)	1190
G^{CNT} (GPa)	17.2	ν^M	0.3
ρ^{CNT} (GPa)	1400		
ν^{CNT}	0.19		

The table 4 presents the first non-dimensional fundamental frequency ($\bar{\omega} = \omega L \sqrt{\rho^M / E^M}$) for three patterns of CNT distribution (UD-CNT, O-CNT, and X-CNT) and two values of (V_{CNT}^*) with ($L/h = 15$). It can be seen from the table that the results of our theory are largely consistent with the third-order shear deformation theory results. In addition, our theory gives better results than classical beam and first-order shear theories in describing mechanical behavior. We also notice from the table that the effect of the third distribution (X-CNT) affects the frequencies significantly compared to the first and second distributions (UD-CNT and O-CNT). Moreover, an increase in the value of (V_{CNT}^*) causes an increase in fundamental frequencies.

Table 4. The first non-dimensional fundamental frequency ($\bar{\omega} = \omega L \sqrt{\rho^M / E^M}$) for three patterns of CNT distribution (UD-CNT, O-CNT, and X-CNT) and two values of (V_{CNT}^*) with ($L/h = 15$).

Theories	Patterns of CNT distribution ($V_{CNT}^* = 0.17$)		
	UD-CNT	O-CNT	X-CNT
Euler–Bernoulli beam theory [3]	1.3868	0.9906	1.6877
Timoshenko beam theory [3]	1.1977	0.9145	1.3796
Third-order shear deformation theory [3]	1.1983	0.9088	1.3760
Present high-order shear deformation theory	1.1988	0.9082	1.3768
	Patterns of CNT distribution ($V_{CNT}^* = 0.28$)		
	UD-CNT	O-CNT	X-CNT
Euler–Bernoulli beam theory [3]	1.7392	1.2391	2.1153
Timoshenko beam theory [3]	1.4348	1.1176	1.6409
Third-order shear deformation theory [3]	1.4361	1.1150	1.6113
Present high-order shear deformation theory	1.4368	1.1146	1.6108

6. Conclusion

The current theory outlines a novel trigonometric function for characterizing shear stress distribution, eliminating the need for a shear correction factor. This theory successfully meets the zero traction boundary conditions on both the upper and lower surfaces of the CNTR beam. The trigonometric shear deformation theory involves only four variables in its displacement field. Compared to other shear deformation theories, the proposed hyperbolic theory offers a more comprehensive and accurate representation of transverse shear stress, resulting in superior outcomes when describing the mechanical behavior of CNTR beam.

Author Contributions: Conceptualization, K.M.A. and F.H.; methodology, K.M.A. and F.H.; software K.M.A. and F.H.; validation, K.M.A. and F.H.; formal analysis, K.M.A. and F.H.; investigation, K.M.A. and F.H.; resources, K.M.A. and F.H.; data curation, K.M.A. and F.H.; writing—original draft preparation, K.M.A.; writing—review and editing, F.H.; visualization, K.M.A. and F.H.; supervision K.M.A. and F.H. All authors have read and agreed to the published version of the manuscript.

Funding: This research received no external funding.

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable.

Data Availability Statement: Not applicable.

Conflicts of Interest: The authors declare no conflict of interest.

References

1. Ebrahimi, F.; Rostami, P. Wave propagation analysis of carbon nanotube reinforced composite beams. *The European Physical Journal Plus*, 2018, 133, 1-12. <https://doi.org/10.1140/epjp/i2018-12069-y>
2. Lin, F.; Xiang, Y. Vibration of carbon nanotube reinforced composite beams based on the first and third order beam theories. *Applied Mathematical Modelling*, 2014, 38(15-16), 3741-3754. <https://doi.org/10.1016/j.apm.2014.02.008>
3. Civalek, Ö.; Dastjerdi, S.; Akbaş, Ş. D.; Akgöz, B. Vibration analysis of carbon nanotube-reinforced composite microbeams. *Mathematical Methods in the Applied sciences*, 2021. <https://doi.org/10.1002/mma.7069>
4. Ansari, R.; Hasrati, E.; Shojaei, M. F.; Gholami, R.; Shahabodini, A. Forced vibration analysis of functionally graded carbon nanotube-reinforced composite plates using a numerical strategy. *Physica E: Low-dimensional Systems and Nanostructures*, 2015, 69, 294-305. <https://doi.org/10.1016/j.physe.2015.01.011>
5. Borjalilou, V.; Taati, E.; Ahmadian, M. T. Bending, buckling and free vibration of nonlocal FG-carbon nanotube-reinforced composite nanobeams: exact solutions. *SN Applied Sciences*, 2019, 1, 1-15. <https://doi.org/10.1007/s42452-019-1359-6>
6. Eghbali, M.; Hosseini, S. A. On Moving Harmonic Load and Dynamic Response of Carbon Nanotube-Reinforced Composite Beams using Higher-Order Shear Deformation Theories. *Mechanics Of Advanced Composite Structures*, 2023, 10(2), 257-270. <https://doi.org/10.22075/MACS.2022.28205.1431>
7. Reddy, J. Analysis of functionally graded plates. *International Journal for numerical methods in engineering*, 2000, 47(1-3), 663-684. [https://doi.org/10.1002/\(SICI\)1097-0207\(20000110/30\)47:1/3<663::AID-NME787>3.0.CO;2-8](https://doi.org/10.1002/(SICI)1097-0207(20000110/30)47:1/3<663::AID-NME787>3.0.CO;2-8)
8. Touratier, M. An efficient standard plate theory. *International journal of engineering science*, 1991, 29(8), 901-916. [https://doi.org/10.1016/0020-7225\(91\)90165-Y](https://doi.org/10.1016/0020-7225(91)90165-Y)
9. Karama, M.; Afaq, K. S.; Mistou, S. A new theory for laminated composite plates. *Proceedings of the Institution of Mechanical Engineers, Part L: Journal of Materials: Design and Applications*, 2009, 223(2), 53-62. <https://doi.org/10.1243/14644207JMDA189>
10. Meliani, M. H.; Kenanda, M. A.; Hammadi, F.; Belabed, Z. Free vibration analysis of the structural integrity on the porous functionally graded plates using a novel Quasi-3D hyperbolic high order shear deformation theory. *Frattura ed Integrità Strutturale*, 2023, 17(64), 266-282. <https://doi.org/10.3221/IGF-ESIS.64.18>
11. Kenanda, M. A.; Hammadi, F.; Zakaria Belabed, Y. A. Free Vibration Analysis of Porous FG Nanoplates via a New Nonlocal 2D Trigonometric High-Order Shear Deformation Theory. *Proceedings of the 9th World Congress on Mechanical, Chemical, and Material Engineering (MCM'23)*, Brunel University, London, United Kingdom, August 06-08, 2023. <https://doi.org/10.11159/mmme23.121>
12. Kenanda, M. A.; Hammadi, F.; Belabed, Z. A NOVEL QUASI-3D AND 2D HIGH-ORDER SHEAR DEFORMATION THEORY FOR THE THERMO-MECHANICAL ANALYSIS OF POROUS FUNCTIONALLY GRADED PLATES RESTING ON ELASTIC FOUNDATIONS. *20th International Conference on Experimental Mechanics*, Porto 2-7 July 2023.

Disclaimer/Publisher's Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.