

Abstract

Preformulation studies of polymeric hydrogels with insulin for pharmaceutical applications[†]

Aneta Ostróżka-Cieślik*, Klaudia Birówka and Barbara Dolińska

Department of Pharmaceutical Technology, Faculty of Pharmaceutical Sciences in Sosnowiec, Medical University of Silesia, Kasztanowa 3, 41-200 Sosnowiec, Poland; s77734@365.sum.edu.pl, bdolinska@sum.edu.pl

* Correspondence: aostrozka@sum.edu.pl;

† Presented at the 9th International Electronic Conference on Medicinal Chemistry, 1–30 November 2023;

Available online: <https://ecmc2023.sciforum.net/>.

Abstract: Hydrogels are carriers of active substances often used in pharmaceutical technology. They are biocompatible with human tissues. They show the ability to absorb biological fluids and have the potential to develop new therapies for the treatment of exudative and chronic wounds. Numerous studies support their potential use as hormone carriers. The aim of our research was to develop a hydrogel containing insulin (INS) for administration on the skin. This hormone exhibits reparative and regenerative effects in lesional tissues. Hydrogel carriers of insulin based on hydroxypropyl methylcellulose (HPMC) and hydroxypropyl methylcellulose (HPMC) with chitosan (CTS) were developed. The insulin concentration (Insulatard Penfill, Novo Nordisk Denmark) was 1mg/g of hydrogel. A paddle apparatus (DT 600, ERWEKA GmbH, Germany) equipped with Enhancer Cell type chambers was used for pharmaceutical availability testing. The semipermeable membrane was a Spectra/Por 2 dialysis membrane. Rotational rheometry was used for rheological tests. A Lamy RM 200 Touch laboratory rheometer (Lamy Rheology Instruments, Champagne au Mont d'Or, France) equipped with an MK-CP 2445 measuring system and a CP-1 Plus thermostat was used. Measurements were carried out at 25±1°C. Hydrogel flow curves were determined and the thixotropy effect of the analyzed systems was tested. Graphical and mathematical analysis of the results was carried out using Rheometric-P Software. The study showed that the release of INS from the developed formulations occurred in a prolonged manner. From the HPMC+CTS-based hydrogel formulation, 73% of the INS was released at 6.5 hours, while from the HPMC-based hydrogel, 65% of the INS was released after 5.5 hours. Rheological studies confirmed that the developed hydrogels are non-Newtonian, shear-thinning systems and have a yield stress. The analyzed formulations exhibit thixotropy. After pre-formulation studies, it was concluded that the hydrogels based on HPMC+INS and HPMC+CTS+INS show a high application potential.

Citation: Lastname, F.; Lastname, F.; Lastname, F. Title. *Med. Sci. Forum* **2023**, *2*, x. <https://doi.org/10.3390/xxxxx>

Academic Editor: Firstname Lastname

Published: date

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Copyright: © 2023 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).

Keywords: hydrogel; insulin; hydroxypropyl methylcellulose; chitosan; in vitro drug release study; rheology;

Supplementary Materials:

Author Contributions: Conceptualization, A.O.-C. and B.D.; writing—original draft preparation, A.O.-C., K.B.; writing—review and editing, A.O.-C.; funding acquisition, A.O.-C. All authors have read and agreed to the published version of the manuscript.

Funding: The research was financed by the Medical University of Silesia in Katowice.

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable. 1

Data Availability Statement: The data presented in this study are available on request from the 2
corresponding author. 3

Conflicts of Interest: The authors declare no conflict of interest. 4
5

6