

# Graphene Quantum Dots: Physico-Chemical Characterization and In Vitro Biological Effects †

Miruna-Silvia Stan <sup>1,2,\*</sup>, Beatrice G. Sbarcea <sup>3,\*</sup>, Bogdan Trica <sup>4</sup> and Anca Dinischiotu <sup>1</sup>

<sup>1</sup> University of Bucharest, Faculty of Biology, Department of Biochemistry and Molecular Biology, 91-95 Splaiul Independentei, 050095 Bucharest, Romania; ancadinischiotu@yahoo.com

<sup>2</sup> Department of Science and Engineering of Oxide Materials and Nanomaterials, Faculty of Applied Chemistry and Materials Science, University Politehnica of Bucharest, 1-7 Polizu Street, 011061 Bucharest, Romania

<sup>3</sup> Advanced Materials Department, National Institute for R&D in Electrical Engineering (ICPE-CA), 030138 Bucharest, Romania

<sup>4</sup> The National Institute for Research & Development in Chemistry and Petrochemistry (INCDCP-ICECHIM), 030138 Bucharest, Romania; trica.bogdan@gmail.com

\* Correspondence: miruna.stan@bio.unibuc.ro (M.-S.S.); gabi\_bea@yahoo.com (B.G.B.)

† Presented at the 2nd International Online-Conference on Nanomaterials, 15–30 November 2020; Available online: <https://iocn2020.sciforum.net/>.

Published: 15 November 2020

**Abstract:** Graphene quantum dots (GQDs) represents nanoscale structures with strong quantum property and exceptional photoluminescence properties. These particles have promising applications in nanomedicine, specifically for diagnostics, cargo delivery, photothermal therapy and bioimaging. In this context, we aimed to characterize GQDs available on the market for a further utilization for in vivo purposes. Transmission and scanning electron microscopy (TEM and SEM), and energy dispersive X-ray spectroscopy (EDX) were used to characterize the morphology and elemental composition of GQDs. In addition, the hydrodynamic size and the zeta potential were measured for these nanoparticles. Their biocompatibility was investigated on human fibroblast lung cells (MRC-5 cell line) after 24 and 72 h of incubation with concentrations up to 200 µg/mL of GQDs. TEM images showed graphene sheets with few wrinkle structures, the dots having uniform diameter in the range between 1.0 and 5.0 nm. SEM examination revealed the three-dimensional structure with a sponge-like aspect and pores of various sizes. Their tendency to aggregate provided the formation of aggregates with sizes of hundreds of nanometers, as it was revealed by the hydrodynamic diameter of about 270 nm. A negative zeta potential of −16 mV confirmed the anionic character of GQDs. Concentrations up to 50 µg/mL exhibited a low toxicity in lung cells as revealed by MTT assay and fluorescent microscopy of actin cytoskeleton after both time intervals, confirming a potential further testing on animals for clinical purposes. However, the high doses of GQDs induced cell death and must be avoided in future. Given the new experimental evidences obtained on GQDs, more knowledge has been achieved, which is very useful for prospective research to revolutionize the future of nanomedicine and biotechnology.

**Keywords:** graphene; quantum dots; biocompatibility

---

## 1. Introduction

Graphene quantum dots (GQDs) represents nanoscale structures with strong quantum property and exceptional photoluminescence properties. These particles have promising applications in nanomedicine, specifically for diagnostics, cargo delivery, photothermal therapy and bioimaging. In this context, we aimed to characterize GQDs available on the market for a further utilization for in vivo purposes.


## 2. Materials and Methods

Transmission and scanning electron microscopy (TEM and SEM), and energy dispersive X-ray spectroscopy (EDX) were used to characterize the morphology and elemental composition of GQDs. In addition, the hydrodynamic size and the zeta potential were measured for these nanoparticles. Their biocompatibility was investigated on human fibroblast lung cells (MRC-5 cell line) after 24 and 72 h of incubation with concentrations up to 200  $\mu\text{g}/\text{mL}$  of GQDs.


## 3. Results

TEM images showed graphene sheets with few wrinkle structures, the dots having uniform diameter in the range between 1.0 and 5.0 nm. SEM examination revealed the three-dimensional structure with a sponge-like aspect and pores of various sizes. Their tendency to aggregate provided the formation of aggregates with sizes of hundreds of nanometers, as it was revealed by the hydrodynamic diameter of about 270 nm. A negative zeta potential of -16 mV confirmed the anionic character of GQDs.

Concentrations up to 50  $\mu\text{g}/\text{mL}$  exhibited a low toxicity in lung cells as revealed by MTT assay, phase contrast images (Figure 1) and fluorescent microscopy of actin cytoskeleton (Figure 2) after both time intervals, confirming a potential further testing on animals for clinical purposes. However, the high doses of GQDs induced cell death and must be avoided in future.



**Figure 1.** Phase contrast images of MRC-5 cells incubated with GQDs for 24 h (a) and 72 h (b).



**Figure 2.** Fluorescence images of F-actin in MRC-5 cells incubated with GQDs for 24 and 72 h.

#### 4. Conclusions

Given the new experimental evidences obtained on GQDs, more knowledge has been achieved, which is very useful for prospective research to revolutionize the future of nanomedicine and biotechnology.

**Funding:** M.S. Stan acknowledges the support of the Operational Programme Human Capital of the Ministry of European Funds through the Financial Agreement 51668/09.07.2019, SMIS code 124705.

**Conflicts of Interest:** The authors declare no conflict of interest. The funders had no role in the design of the study; in the collection, analyses, or interpretation of data; in the writing of the manuscript, or in the decision to publish the results.

**Publisher's Note:** MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



© 2020 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).