

Conference Proceedings Paper

Acid-free hydrothermal process for synthesis of bioactive glasses 70SiO₂-(30-x)CaO-xZnO (x=1, 3, 5 mol.%)

Ta Anh Tuan ¹, Elena V. Guseva ¹ and Bui Xuan Vuong ^{2,*}

¹ Faculty of Chemical Technologies, Kazan National Research Technological University, 420015, ul. K. Marksa 68, Kazan, Tatarstan, Russia; taanhtuan84pt@hpu2.edu.vn (T.A.T); leylaha@mail.ru (E.V.G)

² Faculty of Pedagogy in Natural Sciences, Sai Gon University, Ho Chi Minh City, 700000, Vietnam)

* Correspondence: buixuanvuongsgu@gmail.com; Tel.: +8402838354409

Received: date; Accepted: date; Published: date

Abstract: Bioactive glasses 70SiO₂-(30-x)CaO-xZnO (x=1, 3, 5 mol.%) were prepared by the acid-free hydrothermal method in keeping with the green chemical technology. The synthetic glasses were investigated by TG-DSC, BET, XRD, and SEM-EDX. All synthetic glasses present mesoporous structures consisting of aggregates of nano-particles. The bioactivity of synthetic glasses was confirmed through the formation of the hydroxyapatite phase after in vitro experiment in the SBF solution. The effect of Zn addition is shown through the decrease in the bioactivity of synthetic glasses. Additionally, the ICP-OES analysis indicates that the Zn ions were released from the glassy networks during in vitro experiments, and they act as Zn(OH)₂ suspended precipitation to inhibit the apatite deposition. The in vitro experiment in cell culture matter was performed for SaOS₂ and Eahy929 cells. The results confirmed the biocompatibility of synthetic glasses and the role of Zn addition in the proliferation of living cells.

Keywords: bioactive glasses; bioactivity; sol-gel; hydrothermal; in vitro experiment

1. Introduction

For the past five decades, bioactive glasses have been used as artificial bone materials thanks to their typical ability to connect to the natural bone by forming a hydroxyapatite layer during in vitro and in vivo experiments [1]. These biomaterials can be synthesized by using two main methods melting and sol-gel [2]. Recently, the sol-gel method has been widely applied because it has more advantages than the melting method. This method can produce bioactive glasses at moderate temperatures, preventing the final-product loss because of P₂O₅ evaporation. Furthermore, this method is able to synthesize bioactive glasses on nano-scale with mesoporous structures which reinforces the bioactivity of obtained materials [3-4]. To control the bioactivity and biocompatibility of sol-gel glasses, beneficial elements such as Mg, Sr, Al, Cu, Fe, Ag, and Zn have been added [5-11]. Among them, Zn plays an important role in bone formation because of its ability to inhibit the activity of osteoclasts and increase the differentiation of osteoblasts [12-13]. Depending on the content of the doped Zn as well as the composition of the system, the synthetic glass systems exhibit different properties. Bioactive glass 64SiO₂-26CaO-5P₂O₅-5ZnO (mol.%) has been elaborated by A. Balamurugan et al. using the sol-gel method. The authors pointed out that the incorporation of ZnO not only reduce the bioactivity of synthetic glass but also increase the osteoblast proliferation [6]. Abeer M. El-Kady et al. have fabricated various sol-gel glasses 58SiO₂-(33-x)CaO-9P₂O₅-xZnO (x = 1, 3, 5 wt.%) [14]. All synthetic glasses exhibited high porosities, surface areas, and good bioactivity in the SBF test. Ternary 60SiO₂-36CaO-4P₂O₅ (mol.%) and quaternary 60SiO₂-25CaO-11Na₂O-4P₂O₅ (mol.%) sol-gel glasses doped with 0, 1, 5 and 10 mol.% of ZnO have been synthesized by Julian Bejarano [15]. The study indicated the content of doped ZnO influence on

the textures, bioactivity, and compatibility of synthetic glasses. Furthermore, the increase of doped ZnO caused the decrease in formation of apatite mineral on glass surfaces after *in vitro* experiments. Thus, many glass systems containing ZnO have been studied by the sol-gel method. However, most synthesized ZnO-containing glasses used harmful strong acids and bases as catalysts for the hydrolysis process. In our previous study, the acid-free hydrothermal method has been used for synthesized binary bioactive glass with the molar composition of 70%SiO₂-30%CaO [16]. A combination of starting precursors without acid catalysts was heat-treated in a hydrothermal reactor at 150 °C for 24 hours. The obtained product in concentrated gel was dried and sintered at 700 °C during 3 hours. The synthetic glass was an amorphous structure and presented interesting bioactivity. Based on this approach, we synthesize the ternary bioactive glasses 70SiO₂-(30-x)CaO-xZnO (mol.%, x=1, 3, and 5) within the present work.

The effects of ZnO additions on the physical-chemical properties, bioactivities, and biocompatibilities of synthetic bioactive glasses were investigated.

2. Materials and Methods

2.1. Acid-free synthesis of bioactive glasses containing ZnO

New series of bioactive glasses 70SiO₂-(30-x)CaO-xZnO (mol.%, x=1, 3, 5) were synthesized by the hydrothermal method in line with the previous study [16]. Briefly, a mixture of TEOS (Tetraethyl Orthosilicate, Merck, 99.0%), Ca(NO₃)₂·4H₂O (Merck, 100%), Zn(NO₃)₂·6H₂O (Merck, 98%), and H₂O was put into a hydrothermal system consisting of a stainless-steel autoclave with Teflon core. The reactive system was performed at 150 °C for 1 day. The obtained gel was dried at 150 °C to make the ceramic powders. The bioactive glasses were achieved by sintering the powders at 700 °C for 3 hours. We denoted the bioactive glasses 70SiO₂-(30-x)CaO-xZnO with x = 1, 3, and 5 mol.% of ZnO as Bioglass-Z1, Bioglass-Z3, and Bioglass-Z5, respectively.

2.2. *In vitro* test in SBF solution

The bio-mineralization was verified by the immersion of bioactive glasses in the simulated body fluid (SBF) according to the method of Kokubo [17]. The SBF synthetic solution has inorganic ion concentration similar to that of human blood. Glass powder samples with a mass of 125 mg were soaked in 250 mL of SBF at 37 °C with a stirring rate of 120 rpm for 1, 3, 5, and 7 days. At the end of each immersion phase, the powder samples are refined, dried, and used to determine their physical-chemical characterizations. The remaining solutions are served to measure the ionic concentration

2.3. *In vitro* test with cell culture

Two cell lines SaOS₂ and Eahy929 were selected for culturing in DMEM (Dulbecco's Modified Eagle's Medium, Merck) at 37 °C in a humid environment (95% humidity, 5% CO₂) for 24 hours. The test ratio of glass sample/medium was chosen as 0.1 g/mL consistent with the ISO standard 10993-12:2007. The cell viabilities were determined by the MTT method following the previous report [18]

2.4. Physical-chemical characterization

The thermal analysis was performed by employing a Thermogravimetry-Differential Scanning Calorimetry (TG-DSC, Labsys Evo Setaram). The porous properties were determined from the nitrogen adsorption/desorption measurement on a micromeritics porosimeter (Quantachrome Instruments). The X-ray diffraction (XRD, D8-Advance) was served for phase identification. The morphology and elemental composition were investigated by using the Scanning Electron Microscopy (SEM) associated with the Energy Dispersive X-rays Spectroscopy (EDX) (SEM, S-4800, Japan). The ion behavior in SBF fluid was monitored by using the Inductively coupled plasma optical emission spectrometry (ICP-OES, ICP 2060).

3. Results and Discussion

3.1. Thermal behavior

Fig. 1 presents the TG-DSC curves of Bioglass-Z1, Bioglass-Z3, and Bioglass-Z5. All glasses exhibited three mass-losses within the temperature ranges of 30-200, 200-400, and 400-600 °C. The primary mass-loss is characteristic for the removal of physically adsorbed water. This is shown on the DSC curves of the Bioglass-Z1, Bioglass-Z3, and Bioglass-Z5 as the first endothermic peaks centered at 120.1, 127.9, and 142.6 °C, respectively [19]. The second mass-loss with exothermic peaks concentrated at 313.1, 280, and 297.2 °C on the DSC curves of Bioglass-Z1, Bioglass-Z3, and Bioglass-Z5, respectively, is due to the discharge of chemically adsorbed water [20]. The third mass-loss with endothermic peaks centered at 535.4, 511.5, and 516.6 °C on the DSC curves of Bioglass-Z1, Bioglass-Z3, and Bioglass-Z5, respectively, is related to the decomposition of nitrate groups [21]. An exothermic peak without mass-loss at 963.6, 912.2, and 905.2 °C was observed on the DSC curves for Bioglass-Z1, Bioglass-Z3, and Bioglass-Z5, respectively. This corresponds to the phase transition of the glass [21]. The obtained result shows that the phase transition temperature decreased as the ZnO content in the glass increased. This demonstrates the effect of ZnO addition on the thermal properties of synthetic glasses as observed in the previous study [14]. From the thermal analysis, the sintering temperature for synthesis of bioactive glasses was selected at 700 °C.




Figure 1. TG-DSC curves of bioactive glasses $70\text{SiO}_2-(30-x)\text{CaO}-x\text{ZnO}$ (mol.%, $x=1, 3, 5$).

3.2. Phase analysis

XRD patterns of synthetic glasses Bioglass-Z1, Bioglass-Z3, and Bioglass-Z5 are presented in Fig. 2. The obtained result indicated the amorphous nature of all synthetic glasses, no crystalline peaks were observed. As observed, the center of the diffraction halo was shifted to the right as the ZnO content increased from 1 to 5 mol.%. According to previous studies, Zn acts as Si to form up the glassy

network, and can also replace Ca to act as a network modifier [14, 22]. Therefore, this phenomenon can be explained by the successful introduction of Zn^{2+} ions intertwined in the glass networks




Figure 2. XRD patterns of bioactive glasses $70SiO_2-(30-x)CaO-xZnO$ (mol.%, $x=1, 3, 5$).

3.3. Textural characterization

From the nitrogen adsorption/desorption measurement, the mesoporous properties of synthetic bioactive glasses were obtained as shown in the Tab.1. The obtained result indicates that the ZnO addition induced the reduction of porous structures of synthetic bioactive glasses. This is in line with the previous researches, where the authors showed that the incorporation of divalent ions such as Mg, Cu, Sr, or Zn significantly reduced the porous properties of synthetic glasses [23-24]. The presence of Zn ions may disrupt the orderly association of the SiO_4 tetrahedra within the self-assembly reaction, resulting in structural defects of the silica network, leading to the changes in mesoporous structures of synthetic bioactive glasses.

Table 1. Values of specific surface area, pore diameter, and pore volume for synthetic glasses.

Samples	Specific Surface Area (m^2/g)	Pore Diameter (nm)	Pore Volume (cm^3/g)
Bioglass-Z1	133.6	20.8	0.78
Bioglass-Z3	109.5	18.4	0.51
Bioglass-Z5	74.9	18.2	0.34

Fig.3 represents the SEM-EDX analyses of synthetic bioactive glasses. Observing SEM images shows that Bioglass-Z1 exhibited a rough and porous surface while Bioglass-Z3, and Bioglass-Z5 had less porous surfaces. This observation is consistent with the above result obtained from the nitrogen adsorption/desorption analysis, confirming the effect of ZnO addition on the porous structure reduction of synthetic glasses. The EDX analyses confirmed the presence of the Zn element on the structure of synthetic bioactive glasses.




Figure 3. SEM-EDX analyses of bioactive glasses $70\text{SiO}_2-(30-x)\text{CaO}-x\text{ZnO}$ (mol.%, $x=1, 3, 5$).

3.4. Bio-mineralization

Fig.4 shows the XRD patterns of bioactive glasses after immersion 5 days within the SBF solution. Two well-defined peaks at about $2\theta=26^\circ$ (002) and 32° (211) were observed for all glass samples. These characteristic peaks are contributed to the crystalline hydroxyapatite (HA) phase (JCPDS file No. 90432). This confirmed the bioactivity of all synthetic glasses. As increasing the ZnO contents, two characteristic peaks of HA showed less sharpness and lower intensity. The bioactivity of synthetic glasses can be arranged as Bioglass-Z1 > Bioglass-Z3 > Bioglass-Z5. This phenomenon is in line with the result achieved in previous research, confirming the effect of ZnO addition on the bioactivity of synthetic glasses [23, 25].

The SEM micrographs including EDX analyses of bioactive glasses after 5 days of immersion within the SBF solution are shown in Fig.5. The surfaces of all bioactive glasses were covered by uniform, dense crystal layers. From the XRD analyses, this observation confirmed the hydroxyapatite formation on the surfaces of bioactive glasses after in vitro experiment. The HA layer on the surface of Bioglass-Z1 is more clearly defined than that of Bioglass-Z3, and Bioglass-Z5. The EDX analysis of glass samples after 5 days soaking in the SBF solution showed a sharp decrease in Si content because of the dissolution of the glass network. Meanwhile, Ca and P contents of soaked samples increased clearly, confirming the precipitation of Ca^{2+} and PO_4^{3-} ions to create the apatite layer on the surface of bioactive glasses. The molar Ca/P ratios for the samples Bioglass-Z1, Bioglass-Z3, and Bioglass-Z5 are 1.7, 2.2, and 2.8, respectively. The molar Ca/P ratio of hydroxyapatite (HA) is 1.67. Therefore, sample Bioglass-Z1 showed the best forming ability of HA layer compared to samples Bioglass-Z3 and Bioglass-Z5.




Figure 4. XRD patterns of bioactive glasses $70\text{SiO}_2-(30-x)\text{CaO}-x\text{ZnO}$ (mol.%, $x=1, 3, 5$).




Figure 5. SEM-EDX analyses of bioactive glasses $70\text{SiO}_2-(30-x)\text{CaO}-x\text{ZnO}$ (mol.%, $x=1, 3, 5$) after 5 days in SBF solution.

Ionic changes within the SBF solution are associated with the physical-chemical reactions between the Zn-containing bioactive glasses and the physiological medium (Fig. 6). The initial SBF

fluid contains 100 ppm of Ca, 0 ppm of Si, 31 ppm of P, and 0 ppm of Zn. After in vitro experiment, the ionic-exchange behaviors are quite similar for all bioactive glasses. The Ca concentration increased and then decreased. The Si and Zn concentrations increased gradually while the P concentration decreased. The increase in Ca concentration is due to the rapid exchange between the Ca^{2+} ions of the glassy network and H^+ ions in the physiological fluid [1]. Subsequently, the Ca concentration plummeted to achieve saturation at 5 days of immersion. The decrease in Ca concentration is expounded to its consumption to form the mineral HA on the surface of bioactive glasses [1-2]. As well as the decrease of Ca concentration, the P concentration was noted to decrease because of its consumption to form the apatite mineral layer [1-2]. It can be seen that the consumption of Ca and P to form the HA layer of Bioglass-Z1 is the most, followed by Bioglass-Z3, and Bioglass-Z5. The Si concentration increased rapidly on the first day of soaking, then moderately increased to succeed in saturation at 5 days. The increase in Si concentration is explained by the solubility of the glassy network through the discharge of $\text{Si}(\text{OH})_4$ acids while the saturation process corresponds to the self-assembly reactions of the above acids to form the silica SiO_2 layer [1-3]. The amount of Zn released increased within the order Bioglass-Z1, Bioglass-Z3, and Bioglass-Z5, in keeping with the content of ZnO added to the synthetic glasses. According to the literature [23, 26], a component of the Zn ions released will form the $\text{Zn}(\text{OH})_2$ precipitation, which prevents the deposition of HA on the glass surfaces. This is suitable when the precipitation of HA decreases as the concentration of added ZnO increases in synthetic glasses.




Figure 6. Ionic exchange between bioactive glasses $70\text{SiO}_2-(30-x)\text{CaO}-x\text{ZnO}$ (mol.%, $x=1, 3, 5$) and SBF solution.

3.5. Bio-compatibility

Figure 7 shows the cell viability of the SaOS₂ and Eahy929 lines when exposed to the bioactive glasses for 24 hours. Cell viability without glass contact was chosen as the control (100%) [18].

According to the ISO standard 10993-5 (in vitro test for cytotoxicity), cell viability is set as a percentage relative to the control. If the cell viability is a smaller amount than 70%, the material is cytotoxic. Therefore, all synthetic bioactive glasses (Bioglass-Z1, Bioglass-Z3, and Bioglass-Z5) have good biocompatibility. The Bioglass-Z5 exhibits the foremost effective biocompatibility compared with the samples Bioglass-Z3, and Bioglass-Z1. The obtained results are consistent with previous studies, confirming the effect of ZnO addition on the enhancement of cell viabilities [14-15].




Figure 7. Cell viabilities on bioactive glasses $70\text{SiO}_2-(30-x)\text{CaO}-x\text{ZnO}$ (mol.%, $x=1, 3, 5$) for 24 hours.

4 Conclusion

The study confirmed that the acid-free hydrothermal process was suitable for the synthesis of the bioactive glasses $70\text{SiO}_2-(30-x)\text{CaO}-x\text{ZnO}$ (mol.%, $x = 1, 3, 5$). All synthetic glasses have an amorphous nature. The bioactivity of synthetic glasses was confirmed by the formation of a new layer of hydroxyapatite mineral on the surface of the glass samples after in vitro test in SBF liquid. The effectiveness of the ZnO addition was shown by inhibiting the bioactivity of synthetic glasses. In vitro test within the cellular medium has confirmed the good biocompatibility of the synthetic glasses and also the positive effect of ZnO addition on cell viability.

Author Contributions: T.A.T.: Methodology, experimental, analysis; E.V.G.: Methodology, writing, editing; B.X.V.: Writing, analysis, editing.

Conflicts of Interest: The authors declare no conflict of interest

Reference:

1. Hench, L.L. The story of Bioglass. *J. Mater. Sci. Mater. Med* **2006**, *17*, 967–978.
2. Jones, J.R. Review of bioactive glass: From Hench to hybrids. *Act. Biomater* **2013**, *9*, 4457–4486.
3. Owens, G.J.; Singh, R.K.; Foroutan, F.; Alquaysi, M.; Han, C.M.; Mahapatra, C.; Kim, H.W.; Knowles, J.C. Sol-gel based materials for biomedical applications. *Prog. Mater. Sci* **2016**, *77*, 1–79.
4. Zheng, K.; Boccaccini, A.R. Sol-gel processing of bioactive glass nanoparticles: A review. *Adv. Coll. Interf. Sci* **2017**, *249*, 363–373.
5. Sharifianjazia, F.; Parvina, N.; Tahriri, M. Synthesis and characteristics of sol-gel bioactive $\text{SiO}_2\text{-P}_2\text{O}_5\text{-CaO-Ag}_2\text{O}$ glasses. *J. Non-Crys. Sol* **2017**, *476*, 108–113.

6. Balamurugan, A.; et al. Development and in vitro characterization of sol-gel derived CaO-P₂O₅-SiO₂-ZnO bioglass. *Act. Biomater* **2007**, *3*, 255–262.
7. Salman, S.; Salama, S.; Mosallam, H.A. The role of strontium and potassium on crystallization and bioactivity of Na₂O-CaO-P₂O₅-SiO₂ glasses. *Ceram. Inter* **2012**, *38*, 55–63.
8. Kheshen, A.E.; et al. Effect of Al₂O₃ addition on bioactivity, thermal and mechanical properties of some bioactive glasses. *Ceram. Inter* **2008**, *34*, 1667–1673.
9. Errol, M.; Özyuguran, A.; Çelebican, O. Synthesis, Characterization, and In Vitro Bioactivity of Sol-Gel-Derived Zn, Mg, and Zn-Mg Co-Doped Bioactive Glasses. *Chem. Eng. Tech* **2010**, *33*, 1066–1074.
10. Bari, A.; et al. Copper-containing mesoporous bioactive glass nanoparticles as multifunctional agent for bone regeneration. *Act. Biomater* **2017**, *55*, 493–504.
11. Baino, F.; et al. Fe-doped bioactive glass-derived scaffolds produced by sol-gel foaming. *Mater. Lett* **2019**, *235*, Pages 207–211.
12. Hadley, K.B.; Newman, S.M.; Hunt, J.R. Dietary zinc reduces osteoclast resorption activities and increases markers of osteoblast differentiation, matrix maturation, and mineralization in the long bones of growing rats. *J. Nutri. Biochemis* **2010**, *21*, 297–303
13. Popp, J.R.; Love, B.J.; Goldstein, A.S. Effect of soluble zinc on differentiation of osteoprogenitor cells. *J. Biomed. Mater. Res. Part A* **2007**, *81*, 66–769
14. E-Kady, A.E.; Ali, A.F. Fabrication and characterization of ZnO modified bioactive glass nanoparticles. *Ceram. Inter* **2012**, *38*, 1195–1204
15. Bejarano, J.; Caviedes, P.; Palza, H. Sol-gel synthesis and in vitro bioactivity of copper and zinc-doped silicate bioactive glasses and glass-ceramics. *Biomed. Mater* **2015**, *10*, 025001
16. Hoa, B.T.; Hoa, H.T.T.; Tien, N.A.; Khang, N.H.D.; Guseva, E.V.; Tuan, N.A.; Vuong, B.X. Green synthesis of bioactive glass 70SiO₂-30CaO by hydrothermal method, *Mater. Lett* **2020**, *274*, 128032
17. Kokubo, T.; Takadama, H. How useful is SBF in predicting in vivo bone bioactivity, *Biomater* **2006**, *27*, 2907–2915
18. Mosmann, T. Rapid colorimetric assay for cellular growth and survival: application to proliferation and cytotoxicity assays, *J. Immunol. Meth* **1983**, *65*, 55–63
19. Xia, W.; Chang, J.J. Preparation and characterization of nano-bioactive glasses (NBG) by a quick alkali-mediated (sol-gel) method, *Mater. Lett* **2007**, *61*, 3251–3253
20. Saravanapavan, P.; Hench, L.L. Mesoporous calcium silicate glasses. I. Synthesis, *J. Non. Cryst. Sol* **2003**, *318*, 1–13
21. Román, J.; Padilla, S.; Vallet-Regí, M. Sol-gel glasses as precursors of bioactive glass ceramics, *Chem. Mater* **2003**, *15*, 798–806
22. Courthéoux, L.; Lao, J.; Nedelec, J.M.; Jallot, E. Controlled bioactivity in zinc-doped sol-gel-derived binary bioactive glasses, *J. Phys. Chemis. C* **2008**, *112*, 13663–13667
23. Atkinson, I.; et al. Influence of ZnO addition on the structural, in vitro behavior and antimicrobial activity of sol-gel derived CaO-P₂O₅-SiO₂ bioactive glasses, *Ceram. Inter* **2016**, *42*, 3033–3045
24. Wu, C.; Chang, J. Mesoporous bioactive glasses: structure characteristics, drug/growth factor delivery and bone regeneration application, *Interf. Focus* **2012**, *2*, 292–306
25. Erol, M.; Özyuguran, A. Synthesis, Characterization, and In Vitro Bioactivity of Sol-Gel-Derived Zn, Mg, and Zn-Mg Co-Doped Bioactive Glasses, *Chem. Engin. Tech* **2010**, *33*, 1066–1074
26. Oudadesse, H.; Dietrich, E.; Gal, Y.L.; Pellen, P.; Bureau, B.; Mostafa, A.A.; Cathelineau, G. Apatite forming ability and cytocompatibility of pure and Zn-doped bioactive glasses, *Biomed. Mater* **2011**, *6*, 1–9