

Proceedings

Synthesis, Characterization, and Functionalization of Graphene Oxide-Based Nanoplatfoms for Gene Delivery [†]

Julian D. Torres ¹, Juan C. Cruz ^{2,3} and Luis H. Reyes ^{1,*}

¹ Department of Chemical Engineering, Universidad de Los Andes, Cra. 1E No. 19a–40, Bogotá, DC 111711, Colombia; jd.torresv1@uniandes.edu.co

² Department of Biomedical Engineering, Universidad de Los Andes, Cra. 1E No. 19a–40, Bogotá, DC 111711, Colombia; jc.cruz@uniandes.edu.co

³ School of Chemical Engineering and Advanced Materials, The University of Adelaide, Adelaide, SA 5005, Australia

* Correspondence: lh.reyes@uniandes.edu.co

† Presented at the 2nd International Online-Conference on Nanomaterials, 15–30 November 2020; Available online: <https://iocn2020.sciforum.net/>.

Published: 15 November 2020

Abstract: Gene therapy has been considered a promising strategy for treating several inherited diseases and acquired complex disorders. One crucial challenge yet to be solved to ensure the nanomaterials' success in delivering gene therapies is their ability to escape from endosomes. To address this issue, we previously developed magnetite nanoparticles conjugated with the antimicrobial peptide Buforin II, which showed potent translocating and endosomal escape abilities in several cell lines. In this work, we propose developing new cell-penetrating nanoplatfoms by interfacing graphene oxide (GO) with potent translocating peptides to take advantage of already tested and unique peptides as well as the distinctive interactions of GO with the phospholipids of membranes and endosomes. GO was prepared by the modified Hummers' method through the oxidation of graphite sheets. Next, the functionalization of GO was carried out by rendering pendant amine groups to the GO surface. Thermogravimetric analysis (TGA) and Fourier-Transform Infrared spectroscopy were used to corroborate successful functionalization of the nanoplatfom. FTIR analysis exhibited the peaks related to the distinct carboxyl groups of GO and the Si-O bonds after silanization. TGA allowed us to estimate a silanization efficiency of 38%. Future work will be focused on conjugating Buforin II and assessing translocation efficiency by conducting uptake assays in liposomes and various cell lines. Additionally, endosomal escape will be determined via confocal microscopy by labeling the peptide with fluorescent molecules and examining colocalization with the fluorescent marker of endosomes, LysoTracker. By taking advantage of the exceptional qualities in terms of physicochemical, electrical, and optical properties of GO, this study might provide novel strategies to overcome limitations commonly faced, such as low stability of the translocating biomolecules and endosomal entrapment.

Keywords: gene therapy; graphene oxide; functionalization

1. Introduction

Gene therapy has been projected as a promising strategy to treat several genetic disorders and acquired diseases such as autosomal or X-linked recessive single-gene disorders, including Cystic Fibrosis (C.F.), Adenosine Deaminase deficiency (ADA), emphysema, retinitis pigmentosa, sickle cell anemia, phenylketonuria, hemophilia, and Duchenne Muscular Dystrophy (DMD) [1]. Apart from such severe conditions, recent studies have suggested promising treatments for some autosomal

dominant disorders, polygenic disorders, different forms of cancers, vascular disease, neurodegenerative disorders, and inflammatory conditions, among many others [2]. Gene therapy consists of replacing a distorted gene with a healthy one or completing a missing gene to express the required functional protein [3].

Despite potential findings for both in vivo and ex vivo, a major challenge that remains to be overcome is the efficient delivery of the therapies. Only a small part of the delivered genetic cargo reaches the target site [4]. Therefore, there is a need to develop efficient delivery systems. In line with this, viral and non-viral vectors are current approaches to address the issue related to efficient delivery [1,2]. Viral vectors have demonstrated superior efficiencies for the delivery of genetic material, but failure to comply with biosafety requirements has been considered worrisome by regulatory bodies [5]. As a result, non-viral vectors, particularly nanostructured systems, have gained more attention during the last few years due to their lower immune responses, inexpensive preparation, and advantageous properties for assembling customizable and modular gene delivery nanovehicles [6]. A significant hurdle yet to be solved for these types of systems is their ability to escape from endosomes, which are cell compartments that entrap therapeutic molecules after their internalization and eventually degrade them due to the reduction of pH and the action of several enzymes [7].

Recently, we have conjugated magnetic nanoparticles with the antimicrobial peptide Buforin II. Interestingly, the obtained nanobioconjugates exhibited potent translocating and endosomal escape abilities in several cell lines [8]. Thus, the purpose of this work is to extend this approach to other families of nanomaterials to ultimately obtain an ampler variety of platforms available for a rational design of cell-penetrating vehicles to address the need for a more comprehensive set of tissues and diseases. Carbon-based nanomaterials have been considered as an exciting family to be explored [9]. Mainly, graphene oxide (GO) has recently emerged as an attractive material for gene and drug delivery because of its high surface area, and electrical and optical properties [10]. In addition to these benefits, recent reports have demonstrated important advances in the large-scale and high-throughput production of GO with controlled thickness [11–13]. Consequently, this work pursues to put forward a new family of cell-penetrating systems based on GO-based nanoplateforms by interfacing GO with potent translocating peptides.

2. Materials and Methods

GO was synthesized by following the modified Hummers' method [14], which involves the oxidation of graphite sheets as schematized in Figure 1A. Such oxidation was conducted by mixing 0.75 g of graphite sheets and 4.5 g of KMnO_4 in a solution containing H_2SO_4 (90 mL) and H_3PO_4 (10 mL). The reaction mixture was stirred for 12 h at 50 °C. The oxidation was then quenched by rapidly cooling down the mixture to room temperature followed by addition of H_2O_2 for filtering later. Next, exfoliation of GO was carried out to obtain a solid that was cyclically centrifugated at 4000 RPM for 4 h, resuspended in an aqueous solution of HCl and ethanol, and filtered out. Finally, the as-prepared GO was lyophilized and stored at 4 °C until further use.

The functionalization process was conducted by mixing 100 mg of an aqueous solution of GO with 2 mL of tetramethylammonium hydroxide (TMAH) 25% (*v/v*), 50 μL of pure acetic acid, and 1 mL of (3-Aminopropyl) triethoxysilane (APTES) 10% (*v/v*). This strategy was carried out to render free amine groups on GO's surface, as shown in Figure 1B. Next, to remove unused reagents, the resulting mixture was centrifugated and resuspended in distilled water. Finally, functionalized GO (fGO) was lyophilized and stored at 4 °C until further use.

Fourier-Transform Infrared spectroscopy (FTIR) and Thermogravimetric analysis (TGA) were used to confirm surface modification effectiveness.

3. Results

To demonstrate the process of rendering amine groups on the surface of GO, infrared spectra were obtained for GO (black line) and fGO (blue line) samples, as showed in Figure 2. Characteristic groups for GO were detected as follows: The peak detected at about 3300 cm^{-1} is attributed to the O-

H stretching vibrations of hydroxide groups [15]. Moreover, bands observed at about 1100 cm^{-1} and 1750 cm^{-1} correspond to the stretching vibration of epoxy and the stretching vibration of carbonyl groups, respectively [16,17]. After functionalization, it was possible to observe bands at about 1020 , 1180 and 1460 cm^{-1} , attributed to stretching vibration of Si-O-Si, stretching vibration of Si-O-C and stretching vibration of C-N bonds, respectively [16,18]. Furthermore, the efficiency of functionalization with APTES was estimated at 38% through TGA. Profiles of such analysis are shown in Figure 3.




Figure 1. Scheme of the methodology conducted for: (A) Synthesis of GO: Oxidation of graphite sheets is carried out through the action of KMnO_4 , H_2SO_4 and H_3PO_4 . Once the oxidation step is quenched

by cooling down the resulting mixture to room temperature followed by addition of H₂O₂ for later filtering, the mixture was centrifugated to obtain a solid. Such solid was exfoliated by resuspending it in an aqueous solution of HCl and ethanol. Next, the exfoliation step is cyclically repeated by centrifugating, resuspending and filtering. The protocol was based on the Hummer's synthesis [14]; (B) Functionalization of GO: GO as-synthesized was dissolved in an aqueous solution containing TMAH (25% *v/v*), acetic acid and APTES (10% *v/v*). The solution was stirred for one hour at room temperature. The protocol was based on recent studies conducted for magnetic nanoparticles [8].




Figure 2. Infrared spectra for GO (black line) and fGO (blue line). After rendering amine groups on GO's surface, it was possible to observe characteristic peaks at 1020, 1180 and 1460 cm⁻¹ attributed to expected bonds such as Si-O-Si, Si-O-C and C-N respectively.




Figure 3. TGA profiles for GO (black line) and fGO (blue line). Within this temperature range GO lost over 85% of its mass, while fGO lost about 50% of its mass. This indicates that the functionalization process increased the density per weight unit of the functionalized GO. In addition, the difference between both curves gives a measurement of how efficient the functionalization process was.

4. Discussion

To achieve the successful delivery of cargoes, nanomaterials have often been superficially modified to improve their endosomal escape abilities. In this work, the GO surface has been interfaced with the organosilane APTES to rendering free amine groups. This was confirmed qualitatively through FTIR analysis. Furthermore, it was possible to estimate the efficiency of the functionalization by comparing TGA profiles for GO and fGO. This efficiency is comparable to previous reports pursuing different applications such as lead sequestration [19] and protection from corrosive environments [20].

Since we are particularly interested in delivering gene therapies, future work will focus on conjugating Buforin II and evaluating translocation efficiency by conducting uptake experiments in liposomes and various cell lines. We will also determine endosomal escape via confocal microscopy by labeling the peptide with fluorescent molecules and examining colocalization with the fluorescent probe of endosome compartments LysoTracker.

This work is expected to provide an avenue for developing gene delivery systems based on GO-based nanoplatfoms. Moreover, by taking advantage of the great qualities in terms of physicochemical, electrical, and optical properties of GO, this study might provide novel strategies to overcome limitations commonly faced by drug delivery nanocarriers, such as low stability of the translocating biomolecules and endosomal entrapment.

Author Contributions: Conceptualization, J.C.C., and L.H.R.; Methodology, data curation, and data analysis J.D.T.; Formal analysis and investigation, J.D.T.; Validation, J.C.C. and L.H.R.; Writing—original draft preparation, J.D.T.; Writing—review and editing, J.C.C. and L.H.R.; Supervision, J.C.C. and L.H.R. All authors have read and agreed to the published version of the manuscript.

Funding: This work was funded by the Colombian Ministry of Science, Technology, and Innovation (Minciencias) Grant ID 120380763212–PPTA # 8352.

Acknowledgments: The authors would like to thank the Department of Biomedical Engineering, Food and Chemical engineering and the Department of Electrical & Electronics Engineering at Universidad de los Andes for the financial and technical support.

Conflicts of Interest: The authors declare no conflict of interest.

References

1. Nayerossadat, N.; Ali, P.A.; Maedeh, T. Viral and nonviral delivery systems for gene delivery. *Adv. Biomed. Res.* **2012**, *1*, 27.
2. Ibraheem, D.; Elaissari, A.; Fessi, H. Gene therapy and DNA delivery systems. *Int. J. Pharm.* **2014**, *459*, 70–83.
3. Ebara, M.; Uto, K. *Gold Nanomaterials for Gene Therapy*; Elsevier Ltd.: Amsterdam, The Netherlands, 2016.
4. Mady, M.M. Cationic liposomes as gene delivery system. *Afr. J. Pharm. Pharmacol.* **2011**, *5*, 2007–2012.
5. Shirley, J.L.; de Jong, Y.P.; Terhorst, C.; Herzog, R.W. Immune Responses to Viral Gene Therapy Vectors. *Mol. Ther.* **2020**, *28*, 709–722.
6. Malmsten, M. Inorganic nanomaterials as delivery systems for proteins, peptides, DNA, and siRNA. *Curr. Opin. Colloid Interface Sci.* **2013**, *18*, 468–480.
7. Hillaireau, H.; Couvreur, P. Nanocarriers' entry into the cell: Relevance to drug delivery. *Cell. Mol. Life Sci.* **2009**, *66*, 2873–2896.
8. Cuellar, M.; Cifuentes, J.; Perez, J.; Suarez-Arnedo, A.; Serna, J.A.; Groot, H.; Muñoz-Camargo, C.; Cruz, J.C. Novel BUF2-magnetite nanobioconjugates with cell-penetrating abilities. *Int. J. Nanomed.* **2018**, *13*, 8087–8094.
9. Yin, F.; Gu, B.; Lin, Y.; Panwar, N.; Tjin, S.C.; Qu, J.; Lau, S.P.; Yong, K.-T. Functionalized 2D nanomaterials for gene delivery applications. *Coord. Chem. Rev.* **2017**, *347*, 77–97.
10. Rahmanian, N.; Eskandani, M.; Barar, J.; Omid, Y. Recent trends in targeted therapy of cancer using graphene oxide-modified multifunctional nanomedicines. *J. Drug Target.* **2016**, *25*, 202–215.

11. de Melo-Diogo, D.; Lima-Sousa, R.; Alves, C.G.; Costa, E.C.; Louro, R.O.; Correia, I.J. Functionalization of graphene family nanomaterials for application in cancer therapy. *Colloids Surf. B Biointerfaces* **2018**, *171*, 260–275.
12. Liu, P.; Wang, S.; Liu, X.; Ding, J.; Zhou, W. Platinated graphene oxide: A nanoplatform for efficient gene-chemo combination cancer therapy. *Eur. J. Pharm. Sci.* **2018**, *121*, 319–329.
13. Marcano, D.C.; Kosynkin, D.V.; Berlin, J.M.; Sinitskii, A.; Sun, Z.; Slesarev, A.; Alemany, L.B.; Lu, W.; Tour, J.M. Improved synthesis of graphene oxide. *ACS Nano* **2010**, *4*, 4806–4814.
14. Zawisza, B.; Baranik, A.; Malicka, E.; Talik, E.; Sitko, R. Preconcentration of Fe(III), Co(II), Ni(II), Cu(II), Zn(II) and Pb(II) with ethylenediamine-modified graphene oxide. *Microchim. Acta* **2016**, *183*, 231–240.
15. Bouazizi, N.; Vieillard, J.; Bargougui, R.; Couvrat, N.; Thoumire, O.; Morin, S.; Ladam, G.; Mofaddel, N.; Brun, N.; Azzouz, A.; et al. Entrapment and stabilization of iron nanoparticles within APTES modified graphene oxide sheets for catalytic activity improvement. *J. Alloys Compd.* **2019**, *771*, 1090–1102.
16. Leaper, S.; Abdel-Karim, A.; Faki, B.; Luque-Alled, J.M.; Alberto, M.; Vijayaraghavan, A.; Holmes, S.M.; Szekely, G.; Badawy, M.I.; Shokri, N.; et al. Flux-enhanced PVDF mixed matrix membranes incorporating APTS-functionalized graphene oxide for membrane distillation. *J. Memb. Sci.* **2018**, *554*, 309–323.
17. Shahidi, F.; Arachchi, J.K.V.; Jeon, Y.J. Food applications of chitin and chitosans. *Trends Food Sci. Technol.* **1999**, *10*, 37–51.
18. Sun, W.; Wang, L.; Wu, T.; Wang, M.; Yang, Z.; Pan, Y.; Liu, G. Inhibiting the corrosion-promotion activity of graphene. *Chem. Mater.* **2015**, *27*, 2367–2373.
19. Diagboya, P.N.; Mmako, H.K.; Dikio, E.D.; Mtunzi, F.M. Synthesis of amine and thiol dual functionalized graphene oxide for aqueous sequestration of lead. *J. Environ. Chem. Eng.* **2019**, *7*, 103461.
20. Ramezanzadeh, B.; Ahmadi, A.; Mahdavian, M. Enhancement of the corrosion protection performance and cathodic delamination resistance of epoxy coating through treatment of steel substrate by a novel nanometric sol-gel based silane composite film filled with functionalized graphene oxide nanosheets. *Corros. Sci.* **2016**, *109*, 182–205.

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



© 2020 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).