

Proceedings

Graphene Oxide-THEIC-ECH-Chitosan Network Nanocomposite: A Novel, Efficient and Recyclable Catalyst for Green Synthesis of Polyhydroquinoline Derivatives [†]

Reza Mohamadiani, Mohammad G. Dekamin *, Negin Rostami, Ehsan Valiey and Mohammad Eslami

Pharmaceutical and Heterocyclic Compounds Research Laboratory, Department of Chemistry, Iran University of Science and Technology, Tehran 16846-13114, Iran;

* Correspondence: mdekamin@iust.ac.ir; Tel.: +98-21-77-240-284; Fax: +98-21-73-021-584

† Presented at the 24th International Electronic Conference on Synthetic Organic Chemistry, 15 November–15 December 2020; Available online: <https://ecsoc-24.sciforum.net/>.

Published: date

Abstract: In this present research, two linkers have been utilized for the covalent attachment of graphene oxide with chitosan. Graphene oxide (GO) and chitosan (Cs) were crosslinked by using 1,3,5-tris(2-hydroxyethyl) isocyanurate (THEIC) and epichlorohydrin (ECH) which resulted in forming the expected biopolymer network nanocomposite. The obtained network was characterized by Fourier transform infrared (FTIR) spectroscopy, scanning electron microscopy (SEM), X-ray diffraction (XRD), energy dispersive X-ray spectroscopy (EDS) and thermal gravimetric analysis (TGA) technique. The catalytic application of the GO-THEIC-ECH-Cs nanocatalyst was then investigated in one-pot four-component Hantzsch condensation reaction for the synthesis of polyhydroquinoline derivatives in EtOH under reflux conditions. The obtained results indicated that the applied catalyst in this study exhibited some significant advantages such as reusability and highly efficiency, stability, low required loading, avoiding the use of toxic transition metals, short reaction times, higher yields, easy separation and purification of the products.

Keywords: chitosan; graphene oxide; polyhydroquinoline; biopolymeric network; nanocomposite; heterogeneous catalysis; green chemistry

1. Introduction


Multicomponent reactions (MCRs) have emerged as important organic synthesis approaches which involve reactions of three or more reactants come together in a single reaction vessel to form new products that have portions of all the components. MCRs strategies grant remarkable advantages over conventional bimolecular reactions owing to their convergence, atom-economy, operational simplicity, structural diversity and short synthetic pathway. MCRs have recently gained a new dimension in the field of designing methods to produce elaborate biologically active compounds and new molecular frameworks for potential drugs with diverse pharmacological activities [1,10,16].

Nowadays, nanocomposites are known as the hot topics among chemists, physicists, biologists and other scientists because of their novel and unique applications in various fields. We are living in an era in which everything is becoming smaller and smaller in size with improvements in properties. Using these composites especially in organic reactions appears to be essential and important. For comprehending the importance of the issue, we have introduced a green nanocomposite that has valuable properties such as thermal stability, mechanical strength and a wide surface.

Graphene, as a new type of nanocarbon material, has received a lot of interest among researchers from different fields in this regard. Graphene oxide (GO) is a derivative of graphene and it has two dimensional oriented structure with good chemical stability and other excellent properties [2–4]. This material also has a high theoretical surface area of $2600 \text{ m}^2 \text{ g}^{-1}$ [5]. Sheets of graphene oxide possess numerous oxygen containing functional groups: hydroxyl and carboxylic acid groups are located around the edges, whereas carbonyl and epoxide groups are in the center. The existence of various types of hydrophilic groups allows graphene oxide to be easily exfoliated when it is in the wet state. These active groups can be used to induce chemical reactions and provide graphene oxide with additional functional groups after the modification, therewith, increasing the flexibility and diversity of graphene oxide applications. For example, graphene oxide layers can be intercalated or cross-linked with primary aliphatic amines, alcohols amino acids, diaminoalkanes, boronates, acyl chloride, and isocyanates, or they can be covalently linked with polymers through proper chemical reactions such as esterification or chelation [6,7,11,16]. Furthermore, chitosan is the second abundant natural biopolymers on the earth which has been used widely for different applications [8–10].

There have been a few reports on graphene based chitosan composite with enhanced mechanical properties but these studies involved simple physical mixing of two components [12–15]. To the best of our knowledge, the covalent functionalization of chitosan with graphene oxide achieved by employing 1,3,5-tris(2-hydroxyethyl) isocyanurate (THEIC)-epichlorohydrin (ECH), as linkers, simultaneously has not been reported yet. In this present study, GO and chitosan are crosslinked by using THEIC and ECH to form the expected biopolymer network nanocomposite.

It is believed that the applied catalyst in this study has some significant advantages such as reusability and highly efficiency, stability, low required loading, avoiding the use of toxic transition metals, short reaction times, higher yields, easy separation and purification of the products. Herein, we report our results for a one-pot Synthesis of polyhydroquinoline derivatives using GO-THEIC-ECH-Cs (1) as a highly efficient metal free organocatalyst.



Scheme 1. Synthesis of polyhydroquinoline derivatives catalyzed by GO-THEIC-ECH-Cs (1).

2. Experimental

2.1. General

Reagents and Apparatus

All chemical materials were obtained from commercial suppliers and purchased from the international chemical companies including Merck, Sigma-Aldrich and Fluka. Chitosan (MW = 100,000–300,000 Da) was purchased from Acros Organics. Melting points were measured on an Electrothermal 9100 apparatus and are uncorrected. The analytical thin layer chromatography (TLC) examination were accomplished using Merck 0.2 mm silica gel 60 F-254 Al-plates.


2.2. General Procedure for the Synthesis of Polyhydroquinoline Derivatives (6a–d) by GO-THEIC-ECH-Cs Nanocatalyst

The reaction between 1.0 mmol dimedone, 1.0 mmol aryl aldehyde, 1.0 mmol ethyl acetoacetate, 2.0 mmol ammonium acetate and 1.0 mg of GO-THEIC-ECH-Cs nanocatalyst in 5 mL of EtOH under refluxing conditions was performed for the synthesis of polyhydroquinoline derivatives.

The progress of the reaction was monitored by thin layer chromatography (TLC, (ethyl acetate/n-hexane 1/3). The mixture was then given time to complete the reaction process. The heterogeneous bionanocomposite was separated from the main product by adding hot EtOH and subsequent filtration. The recycled bionanocomposite was washed with acetone and n-hexane, dried and reused four times in subsequent reactions. Then isolated products were recrystallized using EtOH and EtOAc.

3. Results and Discussion

The catalytic activity of GO-THEIC-ECH-Cs (1) was evaluated in the green synthesis of polyhydroquinoline derivatives by condensing dimedone, aryl aldehyde derivatives, ethyl acetoacetate and ammonium acetate in EtOH at reflux temperature. According to Scheme 2, using a small amount of GO-THEIC-ECH-Cs (1), as heterogeneous catalyst (about 10 mg), the desired products were synthesized with high yield and in short time. The ability to separate and recycle the catalyst easily from the reaction mixture with minimal effort is another advantage of this bio-based organocatalyst. This catalyst reused for at least 5 runs without significant loss of catalytic activity.



Scheme 2. Scope of polyhydroquinoline derivatives (6a–d) prepared in the presence of GO-THEIC-ECH-Cs (1).

4. Conclusions

In summary, the biopolymer network nanocomposite was prepared by using THEIC and ECH to crosslink graphene oxide and chitosan. The catalytic application of the GO-THEIC-ECH-Cs nanocatalyst was investigated in one-pot four-component Hantzsch condensation reaction for the synthesis of polyhydroquinoline derivatives in EtOH under reflux conditions. The obtained results indicated that the applied catalyst in this study exhibited some the significant advantages such as reusability and highly efficiency, stability, low required loading, avoiding the use of toxic transition

metals, short reaction times, higher yields, easy separation and purification of the products. Also, this catalyst reused for at least five runs without significant loss of catalytic activity.

Acknowledgments: We are grateful for the financial support from The Research Council of Iran University of Science and Technology (IUST), Tehran, Iran (Grant no. 160/19108).

References

1. Dömling, A.; Wang, W.; Wang, K. *Chem. Rev.* **2012**, *112*, 3083.
2. Dekamin, M.G.; Eslami, M.B.; Maleki, A. Potassium phthalimide-N-oxyl: A novel, efficient, and simple organocatalyst for the one-pot three-component synthesis of various 2-amino-4H-chromene derivatives in water. *Tetrahedron* **2013**, *69*, 1074–1085, doi:10.1016/j.tet.2012.11.068.
3. Compton, O.C.; Jain, B.; Dikin, D.A.; Abouimrane, A.; Amine, K.; Nguyen, S.T. Chemically Active Reduced Graphene Oxide with Tunable C/O Ratios. *ACS Nano* **2011**, *5*, 4380–4391, doi:10.1021/nn1030725.
4. Dikin, D.A.; Stankovich, S.; Zimney, E.J.; Piner, R.D.; Dommett, G.H.B.; Evmenenko, G.; Nguyen, S.T.; Ruoff, R.S. Preparation and characterization of graphene oxide paper. *Nat. Cell Biol.* **2007**, *448*, 457–460, doi:10.1038/nature06016.
5. Dreyer, D.R.; Park, S.; Bielawski, C.W.; Ruoff, R.S. The chemistry of graphene oxide. *Chem. Soc. Rev.* **2010**, *39*, 228–240.
6. Stampfer, C.; Guettinger, J.; Hellmüller, S.; Molitor, F.; Ensslin, K.; Ihn, T. Energy Gaps in Etched Graphene Nanoribbons. *Phys. Rev. Lett.* **2009**, *102*, 056403, doi:10.1103/physrevlett.102.056403.
7. Hu, X.; Wang, J.-S.; Liu, Y.-G.; Li, X.; Zeng, G.-M.; Bao, Z.-L.; Zeng, X.-X.; Chen, A.; Long, F. Adsorption of chromium (VI) by ethylenediamine-modified cross-linked magnetic chitosan resin: Isotherms, kinetics and thermodynamics. *J. Hazard. Mater.* **2011**, *185*, 306–314, doi:10.1016/j.jhazmat.2010.09.034.
8. Cai, X.; Tong, H.; Shen, X.; Chen, W.; Yan, J.; Hu, J. Preparation and characterization of homogeneous chitosan–polylactic acid/hydroxyapatite nanocomposite for bone tissue engineering and evaluation of its mechanical properties. *Acta Biomater.* **2009**, *5*, 2693–2703, doi:10.1016/j.actbio.2009.03.005.
9. Dekamin, M.G.; Azimoshan, M.; Ramezani, L. Chitosan: A highly efficient renewable and recoverable biopolymer catalyst for the expeditious synthesis of α -amino nitriles and imines under mild conditions. *Green Chem.* **2013**, *15*, 811–820.
10. Dekamin, M.G.; Kazemi, E.; Karimi, Z.; Mohammadalipoor, M.; Naimi-Jamal, M.R. Chitosan: An efficient biomacromolecule support for synergic catalyzing of Hantzsch esters by CuSO₄. *Int. J. Biol. Macromol.* **2016**, *93*, 767–774, doi:10.1016/j.ijbiomac.2016.09.012.
11. Goddard, J.-P.; Malacria, M.; Ollivier, C. *Multi-Component Reactions in Molecular Diversity*; Wiley Online Library: Hoboken, NJ, USA, 2020.
12. Dekamin, M.G.; Mehdipoor, F.; Yaghoubi, A. 1,3,5-Tris(2-hydroxyethyl)isocyanurate functionalized graphene oxide: a novel and efficient nanocatalyst for the one-pot synthesis of 3,4-dihydropyrimidin-2(1H)-ones. *New J. Chem.* **2017**, *41*, 6893–6901, doi:10.1039/C7NJ00632B.
13. Ishani, M.; Dekamin, M.G.; Alirezvani, Z. Superparamagnetic silica core-shell hybrid attached to graphene oxide as a promising recoverable catalyst for expeditious synthesis of TMS-protected cyanohydrins. *J. Colloid Interface Sci.* **2018**, *521*, 232–241, doi:10.1016/j.jcis.2018.02.060.
14. Banakar, S.H.; Dekamin, M.G.; Yaghoubi, A. Selective and highly efficient synthesis of xanthenedione or tetraketone derivatives catalyzed by ZnO nanorod-decorated graphene oxide. *New J. Chem.* **2018**, *42*, 14246–14262, doi:10.1039/c8nj01053f.
15. Davoodi, F.; Dekamin, M.G.; Alirezvani, Z. A practical and highly efficient synthesis of densely functionalized nicotinonitrile derivatives catalyzed by zinc oxide-decorated superparamagnetic silica attached to graphene oxide nanocomposite. *Appl. Organomet. Chem.* **2019**, *33*, e4735, doi:10.1002/aoc.4735.
16. Ngah, W.W.; Fatinathan, S. Adsorption of Cu(II) ions in aqueous solution using chitosan beads, chitosan–GLA beads and chitosan–alginate beads. *Chem. Eng. J.* **2008**, *143*, 62–72, doi:10.1016/j.cej.2007.12.006.
17. Jung, C.; Heo, J.; Han, J.; Her, N.; Lee, S.-J.; Oh, J.; Ryu, J.; Yoon, Y. Hexavalent chromium removal by various adsorbents: Powdered activated carbon, chitosan, and single/multi-walled carbon nanotubes. *Sep. Purif. Technol.* **2013**, *106*, 63–71, doi:10.1016/j.seppur.2012.12.028.
18. Li, Q.; Zhou, J.; Zhang, L. Structure and properties of the nanocomposite films of chitosan reinforced with cellulose whiskers. *J. Polym. Sci. Part B Polym. Phys.* **2009**, *47*, 1069–1077, doi:10.1002/polb.21711.
19. Darder, M.; Colilla, A.M.; Ruiz-Hitzky, E. Biopolymer–Clay Nanocomposites Based on Chitosan Intercalated in Montmorillonite. *Chem. Mater.* **2003**, *15*, 3774–3780, doi:10.1021/cm0343047.

20. Alirezvani, Z.; Dekamin, M.G.; Valiey, E. New Hydrogen-Bond-Enriched 1,3,5-Tris(2-hydroxyethyl) Isocyanurate Covalently Functionalized MCM-41: An Efficient and Recoverable Hybrid Catalyst for Convenient Synthesis of Acridinedione Derivatives. *ACS Omega* **2019**, *4*, 20618–20633, doi:10.1021/acsomega.9b02755.

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



© 2020 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).